

PRODUCT SPECIFICATION



The mark of
responsible forestry
FSC® C117321

VIP KRAFT MF

R

Wood-free wrapping/packaging, one-side calendered paper;
made from bleached kraft sulphate pulp.

PROPERTY		UNIT	VALUE												
Grammage	ISO 536	g/m ²	36	38	40	42.5	45	50	52	55	60	70	80	±3%	
Moisture	ISO 287	%	6.5											*	
Tearing resist. (m.d.)	ISO 1974	mN	270	300	330	370	430	440	485	665	695		*		
Tearing resist. (c.d.)	ISO 1974	mN	355	400	420	450	600	600	680	765	815		*		
Burst	ISO 2758	KPa	140	160	165	170	175	180	185	195	245	275	*		
Breaking strength	ISO 1924	N	45		51		58		65		80		*		
Brightness (R 457)	ISO 2470	%	84.5											*	
Colour	ISO 5631-2														
L														94	*
a														-0.3	*
b														1.0	*
Roughness Bendtsen	ISO 8791-2	ml/min	100-300												
Cobb H ₂ O (60s)	ISO 535	g/m ²	25											*	

* Typical values

OTHER CHARACTERISTICS

Reel dimensions:

- a) width (cm): 30-196 (combination of max. 9 reels)
- b) diameter (mm): max. 1250

Reel marks:

- a) inner side: unwinding direction mark
- b) joints – marked: max. 2 per reel
- c) outer side: producer's name, paper grade, order, reel No., grammage (g/m²), reel width & diameter (cm), reel length (m), core diameter (cm), gross weight (kg), PM, PO, date

Sheet dimensions:

A1 (B1) – A0 deviations according to the ISO 216 Standard

Pallet marks:

producer's name, paper grade, order, pallet No., sheet size (mm), grain direction, grammage (g/m²), number of sheets, PO, theor. & gross & net weight (kg)

APPLICATION

For wrapping/packaging (bags/sacks, laminates, tablecloths, tablemats, board, wrapping paper, pattern paper, protective packaging, etc.) printed in flexo and offset techniques.

PACKING

Reels wrapped in multiple layers of waterproof paper laminate.

NOTES

Ecological grade; ECF; made from ECF / TCF pulp.

FSC®: FSC Mix Credit certified product can be provided upon request.

No optical brightening agents added.

Technology & Development Manager
Danijel Oštir