

PRODUCT SPECIFICATION



The mark of
responsible forestry

FSC® C117321

VIP Greenlabel

Graphic, calendered, semi gloss paper;
made mainly from recycled fibres.

R

PROPERTY	UNIT	VALUE		
Grammage	ISO 536	g/m ²	80**	*
Thickness	ISO 534	µm	80	*
Specific volume	ISO 534	cm ³ /g	0.9–1.1	
Moisture	ISO 287	%	6.5	*
Tearing resist. (m.d.)	ISO 1974	mN	350–400	
Tearing resist. (c.d.)	ISO 1974	mN	450–500	
Burst	ISO 2758	kPa	100	*
Breaking strength	ISO 1924	N	40	*
Brightness (R 457)	ISO 2470	%	75	*
Opacity	ISO 2471	%	97	*
Smoothness Bekk (front/back)	ISO 5627	s	200–250/100–150	
Gloss Lehmann (front)	T 480 om-85	%	20–25	*
Cobb H ₂ O (60s)	ISO 535	g/m ²	30–35 ***	*

* Typical values, ** other grammages possible at customer's request,

*** Cobb 20-25 g/m² possible at customer's request.

OTHER CHARACTERISTICS

Reel dimensions:

- a) width (cm): 25–210
- b) diameter (mm): 1000–1250(1450)
- c) core diameter (mm): 70, 76, 100, 120, 150

Reel marking:

On the header and the running surface: producer's name, paper grade, order, reel No, grammage (g/m²), reel width & diameter (cm), paper length (m), reel position, gross weight (kg), PO, date of production, clamping force (kN), number of glued joints, unwinding direction, barcode, notes at customer's request; possible marking adjustments (paper grade, producer) at customer's request.
Glued joints – marked on the reel: max. 1 per reel.

Sheet dimensions:

A1 (B1) – A0 deviations according to the ISO 216 Standard; sheeting grammages ≥50 g/m²

Pallet marking:

On both sides: producer's name, paper grade, order, pallet No, sheet size (mm), grain direction, grammage (g/m²), number of sheets, PO, gross & net weight (kg), date of production, barcode, possible marking adjustments (paper grade, producer) at customer's request.

APPLICATION

For labels, printed in offset and flexo techniques.

PACKING

Reels wrapped in multiple layers of waterproof paper laminate. Pallets with lids wrapped in transparent PE foil fastened by PET straps.

NOTES

Ecological grade; ECF; made from recycled fibres obtained from recovered paper in deinking process.

FSC®: FSC Mix Credit certified product can be provided upon request.

Krško, 29 August 2023

Head of QM
Aleksandra Račič Kozmus

Technical Director
Milena Resnik